



Testing Methods OEKO-TEX® LEATHER STANDARD

Edition 01.2023

OEKO-TEX[®]
International Association for Research and Testing in the Field of Textile and Leather Ecology.
国际环保纺织和皮革协会

OEKO-TEX° Service GmbH Genferstrasse 23, CH-8002 Zurich +41 44 501 26 00 www.oeko-tex.com



内容

OEKO-TEX® LEATHER STANDARD mark

Testing procedures for authorization to use the 授权使用 OEKO-TEX® LEATHER STANDARD 标识 的检测程序。

Contents

26

27

Colour fatness

27.1 Odour test on the other articles

Odour

1	pH value	1	pH 值
2	Formaldehyde	2	甲醛
2.1	Quantitative determination of the content of	2.1	定量测定游离的和可部分释放的甲醛的含量
	free and partially releasable formaldehyde		
3	Heavy metals	3	重金属
3.1	Extraction with artificial acid sweat solution	3.1	使用人造酸汗液提取
3.2	Total digestion of the samples	3.2	样品的总消解
3.3	Chromium (VI)	3.3	六价铬
4	Pesticides	4	杀虫剂
5	Chlorinated phenols	5	氯化苯酚
6	Phthalates	6	软化剂 (邻苯二甲酸酯)
6.1	Siloxanes	6.1	硅氧烷
7	Organic tin compounds	7	有机锡化合物
8	Short and medium chained chlorinated	8	短链和中链氯化石蜡(SCCP & MCCP)
Ū	paraffins (SCCP & MCCP)	·	
9	Per- and polyfluorinated compounds (PFCs) /	9	全氟和多氟化合物(PFC)/全氟和多氟烷基物
	Per- and polyfluoroalkyl substances (PFAS)		质(PFAS)
10	Dimethylfumarate (DMFu)	10	富马酸二甲酯(DMFu)
11	Human ecologically critical colorants	11	对人类生态至关重要的着色剂
11.1	Cleavable arylamines and aniline	11.1	可裂解的芬芳胺和苯胺
11.2	Dyestuff and pigments with human	11.2	具有人类生态关键特性(过敏性、致癌性)的染
	ecologically critical properties (allergenic,		料和颜料
	carcinogenic		
12	Chlorinated benzenes and toluenes	12	氯化苯和氯化甲苯
13	Polycyclic aromatic hydrocarbons (PAH)	13	多环芳香烃(PAH)
14	Solvent residues	14	溶剂残留
15	UV stabilizers	15	紫外线稳定剂
16	Banned flame retardants	16	禁用阻燃剂
17	Volatile organic compounds (VOCs), glycols,	17	挥发性有机化合物(VOC)、乙二醇、甲酚和氯化
	cresols and chlorinated solvents		溶剂
18	Quinoline	18	喹啉
19	N-nitrosamines and N-nitrosatable	19	N-亚硝胺和 N-亚硝基物质
	substances		
20	Surfactants and wetting agent residues	20	表面活性剂和润湿剂残留(烷基酚、烷基酚聚氧
	(Alkylphenols, Alkylphenol ethoxylates)		乙烯醚)
21	Process preservative agents	21	加工防腐剂
22	N-Methyl-2-pyrrolidone (NMP)	22	N-甲基-2-吡咯烷酮 (NMP)
23	Emission	23	释放
23.1	Quantitative determination of formaldehyde	23.1	空气中释放的甲醛的定量测定
	emitting into the air		
23.2		23.2	使用气相色谱法释放具有挥发性和气味的化合
	by gas chromatography		物
24	Glutaraldehyde	24	戊二醛
25	Phenol and Bisphenols	25	苯酚和双酚
2/	C C	2/	4·

26

27

27.1

色牢度

对其他物品进行气味测试

气味



General remarks

In case an article, which shall be certified according to OEKO-TEX® LEATHER STANDARD, contains also textile and non-textile (e.g. metallic) components, these components are tested according to the conditions and criteria of the OEKO-TEX® STANDARD 100 and the methods used there. For this purpose at this point it is referred to the corresponding documents.

总论

如果根据 OEKO-TEX® LEATHER STANDARD 认证的制品还含有纺织品和非纺织品(如金属)组件,则应根据 OEKO-TEX® STANDARD 100 的条件和标准及其规定的方法对这些组件进行检测。为此,其他相应文件中已对这一规定进行了引用。

Abbreviations

- · AAS atom absorption spectrometer
- · CI chemical ionisation
- · DAD diode array detector
- El electron impact
- · EOS optical emission spectrometry
- · FLD fluorescence detector
- IC ion chromatography
- · ICP inductively coupled plasma
- · GC gas chromatography
- · LC liquid chromatography
- · MS mass spectrometry
- UV/VIS ultraviolet-visible

缩写

- ・ AAS 原子吸收光谱仪
- · CI 化学电离
- ・ DAD 二极管阵列检测器
- ・ EI 电子碰撞
- ・ EOS 发射光谱测定
- ・ FLD 荧光检测器
- ・ IC 离子色谱法
- ・ ICP 电感耦合等离子体
- ・ GC 气相色谱法
- ・ LC 液相色谱法
- ・ MS 质谱分析法
- · UV/VIS 紫外-可见分光光度法

1 pH value

The pH value is determined according to ISO 4045 using purified water as extraction solution.

pH 值

根据 ISO 4045 使用纯净水作为提取液测定 pH 值。

2 Formaldehyde

2.1 Quantitative determination of the content of free and partially releasable formaldehyde

The determination of the free and released formaldehyde is performed according to ISO 17226-1 using an aqueous extraction solution.

甲醛

定量测定游离的和可部分释放的甲醛的含量

根据 ISO 17226-1 使用水性提取溶液对游离甲醛和释放甲醛进行测定。

3 Heavy metals

3.1 Extraction with artificial acid sweat solution

The heavy metals with exception of chromium (VI) are extracted by use of artificial acidic sweat solution according to ISO 17072-1. The extract is analysed by means of ICP-OES, ICP-MS or AAS. Metallic accessories having a surface refinement or coating are subjected additional to a further test for extractable nickel after a pre- treatment (wear and

重金属

使用人造酸汗液提取

根据 ISO 17072-1 使用人造酸汗液提取除铬(VI)之外的重金属。通过 ICP-OES、ICP-MS 或 AAS 分析提取物。 经过表面细化或具有涂层的金属配饰在预处理(根据 EN 12472:1998 进行的磨损和腐蚀,用作其磨损介质)之后须接受可萃取镍的进一步检测。



corrosion according to EN 12472:1998, used for its abrasion medium).

3.2 Total digestion of the samples

The samples are chemically digested using acids to get a clear solution, which is afterwards analysed by means of ICP-OES, ICP-MS or AAS. Different components of the sample, which can be differentiated macroscopically (base material, paints, etc.), are separately digested and analysed. The method is therefore suitable to check the samples for total lead content in reference to the requirement of the American legislation for children's articles (CPSIA, Consumer Product Safety Improvement Act).

3.3 Chromium (VI)

Whenever possible the examination according to ISO 17075-2 (determination by means of ionic chromatography) is performed. When this is not possible, the colorimetric procedure by means of UV/VIS (ISO 17075-1) is performed.

4 Pesticides

The tests for the pesticides which are mentioned in OEKO-TEX® LEATHER STANDARD are performed with cleaned-up extracts by GC-MS and LC-MS.

5 Chlorinated phenols

The tests are performed according to ISO 17070. The substances are stripped off the leather sample by steam distillation. The samples is finally analysed for chlorinated phenols by means of GC-MS(/MS) or GC-ECD.

6 Phthalates

The test is performed by extraction of the testing material with tetrahydrofuran, followed by precipitation of the polymers with n-hexane. The extract is analysed by GC-MS.

6.1 Siloxanes

The test is performed by extraction of the testing material with tetrahydrofuran, followed by precipitation of the polymers with n-hexane. The extract is analysed by GC-MS

7 Organic tin compounds

The method is based on an extraction of the testing material with an ethanol/acetic acid solution and tropolone followed by derivatisation with sodium tetraethylborate. The extract is then analysed by GC-MS.

样品的总消解

使用酸对样品进行化学消解以获得澄清溶液,然后通过 ICP-OES、ICP-MS 或 AAS 对其进行分析。对于能够在宏观上加以区分的不同样品组件(基础材料,油漆等),分别进行消解和分析。因此,根据美国儿童用品法规(CPSIA 消费品安全改进法)的要求,该方法适用于检测样品中的总铅含量。

六价铬

根据 ISO 17075-2(通过离子色谱法测定)进行检测。如果无法做到这一点,则通过 UV/VIS (ISO 17075-1)进行比色测定。

杀虫剂

OEKO-TEX® LEATHER STANDARD 中农药测试是使用 GC-MS 和 LC-MS 净化后的提取物进行的。

氯化苯酚

根据 ISO 17070,这些物质通过蒸汽蒸馏方式从皮革样品上提取出来。最后通过气相色谱法 GC-MS (/MS)或 GC-ECD 对样品进行氯化苯酚分析。

软化剂(邻苯二甲酸酯)

测试是通过用四氢呋喃提取测试物质,然后用正己烷沉淀聚合物来进行的。提取物通过 GC-MS 进行分析。

硅氧烷

该测试方法是使用四氢呋喃提取测试物进行测试, 然后使用正己烷来沉淀聚合物,通过 GC-MS 分析提 取物。

有机锡化合物

该方法基于用乙醇/乙酸溶液和托普隆提取测试物质,然后用四乙基硼酸钠衍生化。提取物通过 GC-MS 进行分析。



8 Short and medium chained chlorinated paraffins (SCCP & MCCP)

短链和中链氯化石蜡(SCCP & MCCP)

The method for the determination of the short and medium chained chlorinated paraffines is based on an extraction of the testing material with dichloromethane/n-hexane, followed by a clean-up and subsequent analysis with GC-MS. For a total analysis (sum of short, medium and long chained chlorinated paraffins) the instrument is operated in the EI mode. CI mode is used for the identification and quantification of the SCCP and MCCP congeners present in the sample.

短链和中链氯化石蜡的方法基于用二氯甲烷/正己烷提取测试物质,然后用 GC-MS 进行净化和分析。对于总体分析(短链、中链和长链氯化石蜡的总和),仪器在 EI 模式下运行。CI 模式用于鉴定和定量样品中存在的短链氯化石蜡和中链氯化石蜡元素。

9 Per- and polyfluorinated compounds (PFCs) / Perand polyfluoroalkyl substances (PFAS)

全氟和多氟化合物(PFC)/全氟和多 氟烷基物质(PFAS)

The method for the determination of PFCs/PFAS is based on an extraction with methanol followed by determination of the PFCs/PFAS by means of LC-MS and GC-MS.

为测定全氟和多氟化合物,测试样品需要使用甲醇萃取。然后通过 LC-MS 和 GC-MS 测定 PFC/PFAS。

10 Dimethylfumarate (DMFu)

富马酸二甲酯(DMFu)

The method bases on an extraction of the samples with acetone. After preconcentration the extracts are analysed with GC-MS.

在富马酸二甲酯测定中,基于用丙酮提取样品。预浓缩后,用 GC-MS 进行分析。

11 Human ecologically critical colorants

对人类生态至关重要的着色剂

11.1 Cleavable arylamines and aniline

可裂解的芬芳胺和苯胺

The tests for azo dyes, which may be cleaved into arylamines with cancerogenic properties are carried out following the official test methods according to ISO 17234-1 and 17234-2. The test for the aromatic amine aniline (cleavable from colorants as well as for the presence as chemical residue in free manner) is carried out together with the analyses of azo dyes.

根据 ISO 17234-1 和 17234-2 的官方测试方法对偶氮染料进行测试,偶氮染料可能裂解成具有致癌特性的芳胺。 芳香胺苯胺(可由着色剂裂解以及以化学残基的方式游离存在)的检测可与偶氮染料分析一起进行。

11.2 Dyestuff and pigments with human ecologically critical properties (allergenic, carcinogenic

具有人类生态关键特性(过敏性、致癌性) 的染料和颜料

The identification and quantification of dyestuff and pigments is made through a hot chlorobenzene extraction followed by detection with LC-DAD or LC-MS.

染料和颜料的测试和定量通过热氯苯萃取进行,然后用 LC-DAD 或 LC-MS 进行检测。



12 Chlorinated benzenes and toluenes

氯化苯和氯化甲苯

The method is based on an ultrasonic bath extraction of the testing materials with dichloromethane. The extracts are analysed by means of GC-MS.

该测试方法是对测试物中氯化苯和甲苯含量的测定,基于用二氯甲烷对测试物进行超声波浴提取,然后通过 GC-MS 分析提取物。

13 Polycyclic aromatic hydrocarbons (PAH)

多环芳香烃(PAH)

The method is based on extraction of the test samples with toluene. The extracts are analysed with GC-MS.

该测试方法基于用甲苯提取测试物,然后通过 GC-MS 分析提取物。

14 Solvent residues

溶剂残留

The method is based on extraction of the test samples with methanol. After preconcentration the extracts are analysed with GC-MS.

该测试方法基于用甲醇提取测试物。预浓缩后,用GC-MS分析提取物。

15 UV stabilizers

紫外线稳定剂

The method bases on an extraction of the test samples with tetrahydrofuran. The extracts are then analysed with LC-DAD, LC-MS or GC-MS.

该测试方法基于用四氢呋喃提取测试物。然后用LC-DAD、LC-MS或GC-MS分析提取物。

16 Banned flame retardants

禁用阻燃剂

The determination of the banned flame retardants is performed by extraction of the test material with toluene. The extract is analysed then by LC-MS and GC-MS.

禁用阻燃剂的测试是通过用甲苯提取测试物来进行。然后提取物使用 LCS-MS 或 GC-MS 进行分析。

17 Volatile organic compounds (VOCs), glycols, cresols and chlorinated solvents

挥发性有机化合物(VOC)、乙二醇、甲酚和氯化溶剂

The sample that is to be analysed for organic volatile compounds, glycols, cresols and chlorinated solvents is baked out by thermodesorption technique. The released substances are enriched on suitable trapping material and afterwards analysed by GC-MS.

采用热解吸技术焙烤含有机挥发性化合物、乙二醇、甲酚和氯化溶剂的待分析样品。将释放的物质富集于合适的捕集材料上,然后采用 GC-MS 进行分析。

18 Quinoline

座啉

The extraction of the samples is done with methanol. The measurement of the of quinoline extracted from the material and is performed in comparison with reference substances by use of LC-MS or GC-MS.

用甲醇提取样品。使用 LC-MS 或 GC-MS 对从材料中提取的喹啉进行测量,并与对照物质进行比较。



19 N-nitrosamines and Nnitrosatable substances

N-亚硝胺和 N-亚硝基物质

The N-nitrosamines and N-nitrosatable substances migrate into a saliva test solution. The N-nitrosatable substances react to N-nitrosamines by acidification. The analysis of the N-nitrosamines and Nnitrosatable substances is done by LC-MS.

亚硝胺和亚硝基物质迁移至唾液测试溶液中。亚硝 基物质通过酸化反应生成亚硝胺。 使用 LC-MS 对亚 硝胺和亚硝基物质进行分析。

20 Surfactants and wetting agent residues (Alkylphenols, Alkylphenol ethoxylates)

表面活性剂和润湿剂残留(烷基酚、烷 基酚聚氧乙烯醚)

The method is based on extraction of the test samples with methanol. The extracts are then analysed with LC-MS and/or GC-MS.

该方法使用甲醇提取测试物。然后使用 LC-MS 和或 GC-MS 分析提取物。

21 **Process preservative agents**

The process preservative agents are extracted in an ultrasonic bath extraction with acetonitrile. The filtered extract is then analysed by HPLC-DAD.

加工防腐剂

使用乙腈超声浴提取法提取加工防腐剂。然后使用 HPLC-DAD 分析过滤后的提取物。

22 N-Methyl-2-pyrrolidone (NMP)

NMP is extracted from the leather samples in an ultrasonic bath with acetone. An aliquot of the extract is then used for a GC-MS analysis.

N-甲基-2-吡咯烷酮 (NMP)

使用丙酮超声浴从皮革样品中提取 NMP。然后将一 份提取物用于 GC-MS 分析。

23 **Emission**

For the determination of emitted chemicals an emission chamber is used. The methods used are based on ISO 16000-3, 16000-6 and 16000-9,

释放

使用释放舱测定释放的化学物质。测定方法基于 ISO 16000-3、16000-6和16000-9。

23.1 Quantitative determination of formaldehyde emitting into the

The sample is conditioned in the emission chamber under defined climatic conditions. After equilibration, the samples are adsorbed on different adsorbents. The analysis can then be performed by UV/VIS spectrometry or according to ISO 16000-3 using LC-DAD or LC-FLD.

空气中释放的甲醛的定量测定

样品在规定的气候条件下放入释放舱中进行调节。 达到平衡后,样品吸附在不同的吸附剂上。然后可 通过 UV/VIS 光谱法或根据 ISO 16000-3 使用 LC-DAD 或 LC-FLD 进行分析。

23.2 Emission of volatile and odorous compounds by gas chromatography

The sample is conditioned in the emission chamber. After equilibration, emitted substances are adsorbed on different adsorbents. The analysis is performed by thermal desorption and GC-MS.

使用气相色谱法释放具有挥发性和气味的化 合物

样品在释放舱中进行调节。达到平衡后,释放的物 质吸附在不同的吸附剂上。通过热脱附技术和 GC-MS 进行分析。



24 Glutaraldehyde

Glutaraldehyde is extracted from the leather samples in the ultrasonic bath with acetone, followed by an analysis through GC-MS.

25 Phenol and Bisphenols

The determination of phenol and bisphenols is performed by extraction of the test material with methanol. The extract is analysed then by HPLC-FLD.

26 Colour fatness

In all the colour fastness tests cited below only the fastness grades with respect to staining of the adjacent fabrics are determined. The basic methods for the performing and evaluating the test are ISO 105-A01 and ISO 105-A03. More specifically, following tests are performed:

- Determination of colour fastness to water according to ISO 11642
- Determination of colour fastness to rubbing according to ISO 11640
- Determination of colour fastness to saliva according to ISO 105-A01
- Determination of colour fastness to perspiration according to ISO 11641

27 Odour

A sample of defined area is conditioned in a desiccator of set humidity and the odour formed is evaluated sensory by a set of test persons.

27.1 Odour test on the other articles

All articles are subjected to a preliminary odour test, which, if failed, stops the certification procedure. The odour from mould, high boiling fractions of petrol (from colour printing), fish (from permanent finishing) or aromatic hydrocarbons will induce a test failure. Moreover, odorants (perfumes) used for removing or covering the smell of a textile material originating from its production (oil, fats, dyestuffs) must not be defected during sensory odour testing.

戊二醛

使用丙酮超声浴从皮革样品中提取戊二醛,然后通过 GC-MS 进行分析。

苯酚和双酚

苯酚和双酚的测定是通过用甲醇提取测试物来进行的。然后通过 HPLC-FLD 分析提取物。

色牢度

在下文提及的所有色牢度测试中,仅测定衬贴织物染色的色牢度等级。开展和评估测试的基本方法依据的是 ISO 105-A01 和 ISO 105-A03。具体开展了以下测试:

- ・ 按照 ISO 11642 进行的耐水色牢度测定
- ・ 按照 ISO 11640 进行的干磨色牢度的测定
- ・ 按照 ISO 105-A01 进行的唾液色牢度的测定
- · 按照 ISO 11641 进行的耐汗渍色牢度测定

气味

将确定范围内的样品放入湿度已设定的干燥器中进行调节,所形成的气味由一组测试人员通过感官进行评估。

对其他物品进行气味测试

所有的物品都要进行初步的气味测试,如未能通过测试,则认证程序将停止。来自霉菌、高沸汽油馏分(彩色印刷)、鱼(持久后整理)或芳香烃的气味会导致测试失败。此外,在感官气味测试过程中,不得检出用于去除或覆盖生产中纺织原料(油、脂肪、染料)气味的香味剂(香精)。